FERROXCUBE

DATA SHEET

4B2Material specification

Supersedes data of September 2004

2008 Sep 01





Material specification


4B2 SPECIFICATIONS

Medium permeability NiZn ferrite for use in RF tuning, especially antenna rods in RFID transponders in automotive applications, and wideband and balun transformers.

SYMBOL	CONDITIONS	VALUE	UNIT
μ_i	25 °C; ≤10 kHz;	250 ± 20 %	
	0.25 mT		
В	25 °C; 10 kHz;	≈ 360	mT
	3000 A/m		
	100 °C; 10 kHz;	≈ 310	
	3000 A/m		
$tan\delta/\mu_i$	25 °C; 3 MHz;	≤ 300 × 10 ⁻⁶	
	0.25 mT		
α_{F}	≤10 kHz; 0.25 mT;		K-1
	−40 to 25 °C	$(-1 \pm 4) \times 10^{-6}$	
	−10 to 55 °C	$(-1 \pm 4) \times 10^{-6}$	
	0 to 25 °C	$(-2.5 \pm 4) \times 10^{-6}$	
	25 to 55 °C	$(2 \pm 4) \times 10^{-6}$	
	25 to 85 °C	$(0.5 \pm 4) \times 10^{-6}$	
ρ	DC; 25 °C	≈ 10 ⁵	Ωm
T _C		≥ 335	°C
density		≈ 4600	kg/m ³







2008 Sep 01 232

Material specification

4B2

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

2008 Sep 01 233